

TECHNICAL DATA SHEET

WIRE ROPE LUBRICANT

Wire ropes contain numerous moving parts which require lubrication. Each time the rope bends or flexes, the internal strands rub together. Whitmore's Wire Rope Lubricant coats these strands to prevent friction and wear. This results in longer wire rope life, less downtime for rope changes and more production.

Whitmore's Wire Rope Lubricant quickly penetrates to the core. This ensures that the rope is lubricated throughout while providing a nondrying, nontacky film on the outside of the rope which protects outer strands from corrosion as well as lubricating the wire rope drums and sheaves.

Whitmore's Wire Rope Lubricant is easily pumpable at temperatures down to -25°F (-35°C). Its nondrying film remains flexible in the most extreme weather conditions which eliminates flaking and peeling.

BENEFITS:

- PROLONGS WIRE ROPE LIFE readily penetrates to the core and lubricates internal strands.
- NONTACKY eliminates dirt pick-up and lubricant sling-off.
- EXTREME LOAD-CARRYING ABILITY extends wire rope life and minimizes downtime.
- AVAILABLE IN AN AEROSOL SPRAY lubricates hard-toreach areas.

APPLICATIONS:

Whitmore's Wire Rope Lubricant can be used to lubricate all sizes of wire rope as well as chains, leaf springs and other applications where a penetrating oil is needed. It may also be applied by hand or automatic lubrication system.

RECOMMENDED APPLICATION RATES:

<u>Drip System</u>: **First Week** - 3 drops per minute per inch diameter rope. **Second Week and Thereafter** - 1 drop per minute per inch diameter rope.

Spray System: Every 15 minutes for 30 seconds (on payout only).

ASTM #		TYPICAL CHARACTERISTICS	
	ISO Grade	22	
D-445	Kinematic Viscosity		
	cSt @ 40°C	22	
	cSt @ 100°C	4	
D-2161	Saybolt Viscosity		
	SUS @ 100°F	118	
	SUS @ 210°F	39	
D-2270	Viscosity Index	25	
D-97	Pour Point, °F (°C)	-40 (-40)	
Gardner	Density , lb/gal @ 60°F (15.5°C)	7.58	
Method	Specific Gravity, g/cc @ 60°F (15.5°C)	0.910	
D-92	Flash Point, °F (°C) Cleveland Open Cup	325 (163)	
D-92	Fire Point, °F (°C) Cleveland Open Cup	360 (188)	
D-2783	Four Ball EP		
	Weld Point, kg	160	
	Load Wear Index	50	
D-4172	Four Ball Wear, Scar Width, mm @ 40 kgf	0.35	
D-665	Rust Test		
	Distilled Water	Pass	
	Synthetic Sea Water	Pass	
D-130	Copper Strip Corrosion	1B	
	212°F (100°C) @ 3 hr		

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

PACKAGING

Shuttle Tanks Nor	onreturnable Totes Drums	Kegs	Pails	Aerosol Cans 12 per case
-------------------	--------------------------	------	-------	-----------------------------

For warranty information, scan the QR code. You can also email us at sales@whitmores.com Or write to the Sales Department at the address below.